

STOPAQ® WRAPPINGBAND CZ

Product Information

Product description: Stopaq® Wrappingband CZ is a low temperature, cold-applied, non-crosslinked, non-crystalline prefabricated monolithic viscous polymer wrap coating with cold flow, self-healing, visco-elastic properties. Stopaq® Wrappingband CZ is a corrosion preventing, non-toxic wrap material adhering extremely well to steel and factory applied pipeline coatings like PE, PP and FBE. Stopaq® Wrappingband CZ is a viscous liquid at the indicated operating temperatures and therefore flows into all irregularities of the substrate. Stopaq® Wrappingband CZ is fully resistant to water and has a very low gas- and water vapour permeability.

Stopaq® Wrappingband CZ requires an additional flexible mechanical protective layer like Stopaq® Outerwrap, eventually followed by a rigid mechanical protective layer like Stopaq® Polyester or Stopaq® Outerglass Shield. Stopaq® Outerwrap improves impact and indentation resistance of such a coating system and results in self-healing of small damages like dents and cuts.

Features:

- Controlled cold flow providing permanent inflow into the finest pores of the substrate.
- Resistance to low temperatures without getting brittle
- Conforms to any shape
- Low surface tension; adheres on all dry substrates at a molecular level
- Surface tolerant: no blasting techniques required, wire brushing is sufficient (ISO 8501-1: St 2)
- Constant film thickness
- Adhesion based on vanderWaals forces
- Inert to ageing and weathering
- Resistant to many chemicals like water, salts, acids, alkalis, polar solvents, etc. For additional information, please consult Stopaq b.v.

Benefits:

- Environmentally friendly, no health and safety hazards to humans
- Fast and easy to apply at low temperatures
- Easy to control during application
- Can be moulded onto various types of irregular shaped objects
- No osmosis or underfilm migration of moisture
- No cathodic disbondment
- Cathodic Protection (CP) of steel structures is not affected
- Guaranteed performance

Product certificate:

- Stopaq® Wrappingband CZ is certified by KIWA according to BRL-K911/02:
"Kiwa Product certificate for corrosion protection compound and tapes for tank and pipeline installations according to the Evaluation Guideline BRL-K911/02 with a verification according to standard EN-12068."
- Stopaq® Wrappingband CZ is certified by DVGW according to DIN 30672.

Application examples

Piping and Vessels: For protection against external corrosion of buried or immersed carbon steel pipelines structures and reservoirs.

Field joints: For protection against external corrosion of buried or immersed carbon steel pipeline girth-weld joints.

Elbows, Bends, Tees and Reducers: For protection against external corrosion of buried or immersed carbon steel pipe fittings.

Pipe coating repair: For repair and rehabilitation and protection against external corrosion of pipeline coating defects.

Product properties of Stopaq® Wrappingband CZ

Colour	Green
Thickness	2.0 ± 0.2 mm
Density	1.5 ± 0.1 g/cm ³ (NEN 1833)
Temperature ranges	Operational temperatures: - 45°C to + 50°C Substrate temperature during application: - 30°C to + 50°C
Elongation	> 100 % (ASTM D1000)
Water absorption	< 0.03% (ASTM D570) *
Permeability	< 0.2 g/m ² /day (ASTM E96)
Glass transition temperature	≤ - 65°C (ISO 21809-3/A1) *
Drip resistance	Tested 72h@+100°C (ISO 21809-3/A1) * : No dripping of compound
Specific electrical insulation resistance	Rs ₁₀₀ > 10 ⁸ Ω.m ² (ISO 21809-3/A1) *
Peel strength test	Tested @+23°C and +50°C (ISO 21809-3/A1) on steel (Sa 2½, St 2 and St 3) and plant coatings (PP, PE and FBE). Results on all substrates: - Cohesive failure - ≥ 99% coverage of surface - ≥ 0.6 mm residual thickness
Thermal ageing resistance and hot water immersion	Ageing 100 days@+70°C, dry and hot water immersion: Results of peel strength test are identical to results obtained with non-aged material.
Lap shear strength	Tested @+23°C and +50°C (ISO 21809-3/A1) on steel (Sa 2½, St 2 and St 3). Results on all substrates: - Cohesive failure - ≥ 99% coverage of surface - ≥ 0.6 mm residual thickness
Resistance to thermal cycling	25 water immersed cycles 9h -30°C to +60°C and back : - Increase of water absorption < 0.07% * - Decrease of elasticity (E-modulus) < 0.07% *

Properties of coating system comprising Stopaq® Wrappingband CZ and Stopaq® Outerwrap PVC

Thickness	3.0 ± 0.2 mm
Impact resistance	Tested @ 15 J (ISO 21809-3/A1) * @ -45°C : no holidays @ +23°C : no holidays @ +50°C : no holidays
Indentation resistance	Tested @ 10 N/mm ² (ISO 21809-3/A1) * @ -45°C : no holidays, residual thickness ≥ 0.6 mm @ +23°C : no holidays, residual thickness ≥ 0.6 mm @ +50°C : no holidays, residual thickness ≥ 0.6 mm
Cathodic disbondment resistance	Tested at +23°C and +50°C (ISO 21809-3/A1) * Disbondment 0 mm, no holiday (defect Ø 6mm self-healed within 1 day)
Self-healing effect	Artificial defect Ø 6mm tested for completion of self-healing effect: @ -45°C : completed < 90 days, no holiday @ +23°C : completed < 24 hours, no holiday @ +50°C : completed < 24 hours, no holiday
Thermal ageing resistance and hot water immersion	Ageing 100 days@70°C, dry and hot water immersed: Results of self-healing effect are identical to results obtained with non-aged material.

* According to BRL-K911/02

Note: ISO 21809-3/A1 = ISO 21809-3:2008/Amendment1:2011

General order information

Product	Stopaq® Wrappingband CZ is available in rolls of various widths and lengths
Art. Nr.	Packing size
4250	50mm x 5m; 24 pcs/box; 576 pcs/pallet
4235	50mm x 10m; 12 pcs/box; 360 pcs/pallet
4240	100mm x 10m; 6 pcs/box; 180 pcs/pallet
6126	200mm x 5m; 2 pcs/box; 96 pcs/pallet
6127	200mm x 10m; 2 pcs/box; 96 pcs/pallet
Handling	Handle with care. Keep boxes upright.
Storage	Store indoor, clean and dry, away from direct sunlight in a cool place at temperatures below +35°C. Unlimited shelf life.

Application instruction: Preparation		Application instruction: Quality control	
Tools, equipment and auxiliaries	<ul style="list-style-type: none"> Temperature probe, Dew point tester, High voltage holiday tester Scissors, Knife, Measuring tape Abrading pads, Wire brushes Isopropyl alcohol, cas. nr. 67-63-0 Personal protective gear 	Visual inspection	The appearance of Stopaq® Wrappingband CZ must look smooth and tight and should be shaped around all details and into corners.
Additional materials	Depending on type of application, various additional materials might be needed: <ul style="list-style-type: none"> Stopaq® Outerwrap PVC / PE Stopaq® Polyester Stopaq® Outerglass Shield 	Holiday detection	Immediately after application of Stopaq® Wrappingband CZ, holiday testing can be carried out with a voltage of 15 kV. A brush probe is recommended. No further testing is required.
High humidity	Stopaq® Wrappingband CZ can be applied in a humid atmosphere. The substrate should be free from condensing water which can be reached by keeping the temperature at least 3°C above dew point.	Application instruction: Mechanical protection	
Work area and substrate	The substrate surface should be dry, clean and protected against negative weather influences.	Mechanical protection	Once applied, Stopaq® Wrappingband CZ should be protected against impacts, indentations, soil pressure and other influences by application of Stopaq® Outerwrap, eventually followed by Stopaq® Polyester or Stopaq® Outerglass Shield. Please consult Stopaq for further information.
Product conditions	Stopaq® Wrappingband CZ should be dry and the temperature should be above + 5°C for the ease of application.	Bringing into service	
		Exposure to loads	Objects coated with Stopaq® Wrappingband CZ should not be exposed to loads e.g. from supports- or lifting equipment.
		Immersion or burying	Immersion or burying is possible immediately after completion of the coating application. Backfill and compact with clean sand and filling material without sharp stones or hard lumps of soil.

Application instruction: Surface preparation	
General	The area to be coated has to be clean, dry, and free from oil, grease and dust. All contamination including mill-scale has to be removed.
Degreasing	Degrease surfaces with isopropyl alcohol and e.g. a lint-free cloth.
Salts and bacteria	No need for additional cleaning.
Condensation of water	Prior to and during the application, the temperature of the substrate(s) must be at least 3°C above the dew point.
Steel	Minimum requirement for surface preparation is St 2 according to ISO 8501-1. Roughness profile is not essential for adhesion.
Bitumen	Remove loose bitumen. For proper adhesion, make sure that the surface is clean and dry. Heating up the surface to +60°C may be required. Avoid recoating of moist bitumen parts.
Other substrates	De-gloss and degrease the surfaces by using an abrasive pad and isopropyl alcohol.
Cleanliness check	Take a piece of Wrappingband of ± 150 mm length, remove the release foil and fold it back for about 25 mm. Put the Wrappingband onto the surface, press it firmly and leave it for 5 minutes. Pull the Wrappingband from the substrate with an angle of app. 135 deg. and a speed of 100 mm/min. Cohesive fracture should occur and coverage of the surface with remaining material should be ≥ 85%. If this is less, surface cleaning is insufficient.
Final control	The substrates prepared for coating, should be clean, dry and free of dust according to ISO 8502-3, grade 3.

Application instruction: Brief version	
Wrapping	Start with removal of a small part of the release liner and apply the Wrappingband on the substrate. Apply Wrappingband without any tension onto the substrate. Avoid air-enclosures. Mould the Wrappingband tight onto the substrate surfaces.
Release foil	Do not remove the release foil before application of the Wrappingband. Remove just prior to application of the Wrappingband to the surface.
Overlap of wraps	Side-by-side overlap: ≥ 10 mm Consecutive rolls: ≥ 50 mm Overlap on factory applied coating: consult specific Stopaq coating instructions.
Specific coating applications	See specific Stopaq coating instructions for e.g. field joints, pipe wrapping, coating repair, etc.

Stopaq® information and warranty	
Documentation	Extensive information is available on our web-site. Application instructions, "Stopaq® Technical Standard" and other documentation can be obtained from our head office, from our local distributor or by email to info@stopaq.com
Certified staff	The application of Stopaq® coating systems should always be carried out by certified personnel.
Stopaq® performance	Extensive laboratory tests and more than 10 years of service in extreme wet and chemical aggressive environments have proven that corrosion, bacterial growth or stress corrosion cracking cannot develop on substrates coated with Stopaq® coating systems.
Long term guarantee	Stopaq® offers a 30 year guarantee on the properties of the Stopaq® materials as described in this document.

DISCLAIMER: To the best of our knowledge, the technical data contained herein is true and accurate on the date of publication and is subject to change without prior notice. User must contact Stopaq B.V. to verify correctness before specifying and ordering. No guarantee of accuracy is given or implied. We do not accept any responsibility for coverage, performance or injuries resulting from use. Liability, if any, is replacement of products. No other warranty or guarantee of any kind is made by Stopaq B.V., express or implied, statutory, by operation of law, or otherwise, including merchantability and fitness for a particular purpose. Stopaq® is a registered trademark of Stopaq B.V.